

Epoxy Control Joint  
Filler and Traffic Loops  
Bonding precast curbing  
and stops

---

Type:	Two-component, solvent-free, epoxy resin I hardener.
Primary Use:	Flexible filler and sealant for sawcut control joints, wire slots and traffic loops. Bonding precast concrete curbing.
Substrates:	Concrete, masonry, stone, asphalt and steel. Dry surfaces only.
Minimum Temp:	Installation- 50 F, Cure- 50 F (substrate temperature).
Finish:	Smooth or variable texture with aggregate broadcast.
Colors:	Black and concrete gray (blue-gray).
Coverage:	As a joint filler, 0.13 cu ft/gal.
Shelf Life:	Three years minimum in sealed containers (see below for conditions).

---

The properties listed in this bulletin are typical and descriptive of the product and should not be used for specification purposes. For specification preparation, reference the specification of this product available from ChemCo Systems, Inc. This product is available only through KIP System™ (KEMKO Injection Process) licensee/applicators.

**Description:** KEMKO 064, Control Joint/Loop Sealant is a two-component, fast curing, flexible, epoxy control joint filler and wire slot and traffic loop sealant. The cured product has excellent impact and energy absorbing properties and is resistant to deicing chemicals and most aircraft and automotive fluids. Its low water absorption and high dielectric strength make it ideally suited for embedding and sealing wire and traffic detection loops in concrete and asphalt pavements and for filling properly prepared sawcut control joints in interior concrete slabs. Additional uses include bonding of precast concrete curbing to concrete and asphalt substrates.

**Features:** Unlike many other flexible, epoxy joint fillers, KEMKO 064 exhibits excellent resistance to water, aqueous salt solutions, most auto and aircraft fluids, does not embrittle when exposed to sunlight for long periods of time and is environmentally safe. It has a convenient 1:1 (by vol.) mixing ratio and is formulated for single pour, high-build applications. The components do not contain volatile solvents (VOC's).

**Limitations:** Substrates must be dry. The minimum substrate temperature during application and initial cure period (18-36 hr) is 50 deg F. KEMKO 064 is not an elastomer and, therefore, is not recommended for use in exterior joint filling applications, expansion joints and joints subject to significant movement or flexing. Do not add solvents or otherwise thin this material.

**Packaging:** Standard package sizes of Part A + Part B are 2, 10 and 100 gallons.

**Shelf Life:** Three years minimum in unopened, original containers when stored between 60 and 90 deg F in a dry place away from sunlight. Remixing of components may be required upon long term storage.

**Chemical Resistance:** KEMKO 064 is resistant to a wide range of commonly used aircraft and automotive chemicals including jet fuels, gasoline, selected hydraulic fluids, anti-freeze and battery acid. It has limited resistance to hydrocarbon solvents.

Performance is a function of the specific chemical and concentration, ambient and solution temperatures, exposure times and housekeeping procedures. For information on specific chemicals and exposure conditions, contact a Chemco Systems, Inc., technical representative.

**Color Selection:** Standard colors are black and concrete gray (blue-gray). Custom colors are available and may require minimum quantities and/or slightly higher cost.

**Surface Preparation:** Substrate surfaces must be dry, sound and free of all bond inhibiting substances. Prepare surfaces for bonding in accordance with ASTM D 4259, 'Standard Practice for Abrading Concrete,' or ACI 503R, Chapter 5, 'Preparing Surfaces for Epoxy Compound Application,' and ChemCo Systems, Inc.'s specific recommendations. Properly prepared concrete surfaces should have a minimum strength of 250 psi in direct tension. Steel surfaces should be cleaned to 'white metal' according to SSPC SP 5.

**Mixing:** KEMKO 064 is a two-component adhesive. The resin to hardener (Part A: Part B) mix ratio is 1:1, by volume. Premix the individual components before drawing from bulk packaging. Wear safety glasses and clean neoprene rubber gloves when handling the material. KEMKO 064 is a short working life/fast curing adhesive. Use quantities that can be applied before the potlife of the mixed material expires. Transfer the appropriate quantities of Part A and Part B into a mixing container. Blend thoroughly using a Jiffy mixer blade attached to a low speed (350-750 rpm) electric or pneumatic drill. Proper mixing will take 2-3 minutes.

**Installing as Control Joint Filler/Loop Sealant:** Transfer mixed material to a pour can with a spout sized for the joint or slot to be filled. Fill the joint in a single application. For a filled surface flush with the surrounding substrate, overfill slightly the joint until a crown of material is formed. Following cure, excess material (high spots) may be removed by warming with a hot air stream (heat gun recommended) and cutting with a sharp blade. For additional application information, see ACI 503R, Chapter 7, "Applying Epoxy Compounds."

**Yield as Joint Filler/Loop Sealant:** The following material estimates do not take into consideration material lost in mixing and application and excess material for overfilling the joint or slot.

Joint Dimensions, inches		Coverage, lineal feet/gallon
width	depth	
1/2	1/4	154
1/2	3/8	102
3/4	3/8	68
3/4	1/2	51
1	3/4	25



**ChemCo Systems, Inc.**

2800 Bay Road

Redwood City, CA 94063

650-261-3790 Fax 650-261-3799

## Typical Properties (1)

Property	Test Method	Value
Mix Ratio, A:B,      by vol by wt		1 : 1 100: 79
Color:    Part A Part B	VISUAL	Blue-gray or black Clear amber
Mixed		Blue-gray or black
Weight per Gallon, lb:    Part A Part B Mixed	ASTM D 1475	9.8 7.8 8.8
Viscosity, cp:    Part A Part B Mixed  4300	ASTM D 2393	4000 4500
Gel Time, 200 g, minutes	ASTM D 2471	16
Tensile Strength, psi	ASTM D 638	1400 (2)
Elongation at Break, %	ASTM D 638	90 (2)
Tear Resistance, lb/in	ASTM D 624	110 (2)

(1) Cure schedule, 7 days at 73 ± 4 F and test temperature, 73 ± 4 F.

(2) Tested at crosshead speed of 2.0 inches/minute.

**Clean-up:** All tools and equipment must be cleaned before the mixed material cures. Cleaning can be facilitated with a solvent such as acetone or heavy duty detergents. Cured material may be removed from equipment and tools by soaking in an epoxy stripper.

**Handling and Toxicity:** This bulletin does not accompany the product when sold. For hazard warnings, safe handling and first aid instructions, READ CAREFULLY THE MATERIAL SAFETY DATA SHEETS AND CONTAINER WARNING LABELS. Part A: Liquid epoxy resin, HMIS Health Hazard Rating- 2 (Moderate Hazard). Warning! Causes eye and skin irritation. May cause allergic skin reaction, Harmful if swallowed. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Avoid prolonged or repeated contact with skin. Part B: Liquid epoxy hardener, HMIS Health Hazard Rating- 2 (Moderate Hazard). Contains alkaline amines. Warning! Causes severe eye and skin irritation, May cause allergic skin and respiratory reaction, Combustible, corrosive. Do not get in eyes or skin or on clothing. Avoid breathing vapor, Keep container closed. Use only with adequate ventilation. Wash thoroughly after handling. Keep away from heat and open flame.

**DISCLAIMER:** NO EXPRESS WARRANTY IS MADE WITH RESPECT TO THE RESULTS OF ANY USE OF THIS PRODUCT. NO IMPLIED WARRANTIES, INCLUDING AND NOT LIMITED TO AN IMPLIED WARRANTY OF MERCHANTABILITY OR AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE ARE MADE WITH RESPECT TO THIS PRODUCT. NO LIABILITIES FOR PERSONAL INJURY, LOSS OR DAMAGE RESULTING FROM THE USE OF THIS PRODUCT IS ASSUMED. CHEMCO SYSTEMS, INC. RESERVES THE RIGHT TO ALTER OR DISCONTINUE THE PRODUCT DESCRIBED HEREIN AT ANY TIME AND WITHOUT PRIOR NOTICE.

KEMCO® and KIP System™ are tradenames of ChemCo Systems, Inc.

Publication Number: 6 EP KEM-114L, Control Joint/Loop Sealant

Publication Date: Nov. 1995