

---

Type:	Two-component, solvent-free, epoxy resin / hardener.
Primary Uses:	Impact, abrasion and skid resistant surfacing.
Substrates:	Concrete, asphalt and steel. Dry surfaces only.
Minimum Temp:	Installation 50 F; Cure-50 F (substrate temperatures).
Thickness:	Single or multiple coats @ 6-10 mils per coat.
Finish:	Smooth or variable texture with aggregate broadcast.
Colors:	Black and concrete gray.
Coverage:	As a surfacing, 80-125 sq ft / gal. (multiple coats)
Shelf Life:	Three years minimum in sealed containers (see below for conditions).

---

The properties listed in this bulletin are typical and should not be used for specification purposes. For specification preparation, reference the specification guideline available from ChemCo Systems, Inc. This product is available only through KIP System™ (Kemko injection process) applicators.

**Description:** Kemko 064 LV Utility Coat is a two-component, fast curing, flexible, low viscosity epoxy coating with resistance to most oils, greases and automotive chemicals. When seeded or blended with aggregate, it can be used on properly prepared asphalt and concrete pavements and on steel decks to provide a pedestrian or vehicular traffic surface with excellent slip/skid resistance and wear characteristics.

**Features:** Unlike many other flexible, exterior coatings, Kemko 064 LV Utility Coat exhibits excellent resistance to water, aqueous salt solutions and motor fuels, does not embrittle when exposed to sunlight for long periods of time and is environmentally safe. It has a convenient 1:1 (by vol.) mixing ratio and is formulated for multiple coat, low-build applications. It contains no volatile solvents (VOC's).

**Limitations:** Substrates must be dry. The minimum substrate temperatures during application and initial cure period (18-36 hr) is 50 F. Apply the material after the daily substrate temperature cycle has reached its peak. Substrates on or below grade must have a functioning vapor barrier to minimize the potential for blistering or delaminating of the applied coating.

**Packaging:** Standard package sizes of Part A + Part B are 2, 10 and 100 gallon units.

**Shelf Life:** Three years minimum in unopened, original containers when stored at room temperature in a dry place away from sunlight. Remixing of components may be required upon prolonged storage.

**Chemical Resistance:** Kemo 064 LV Utility Coat is resistant to a wide range of commonly used aircraft and automotive chemicals including jet fuels, gasoline, selected hydraulic fluids, anti-freeze battery acid and most alkalies. It has limited resistance to hydrocarbon solvents. Performance is a function of the specific chemical and concentration, ambient and solution temperatures, residence times and housekeeping procedures. For information on specific chemicals and exposure conditions, contact a ChemCo Systems, Inc., technical representative.

**Color Selection:** Standard colors are black and concrete gray. Custom colors are available and may require minimum quantities and/or slightly higher cost.

**Surface Preparation:** Substrate surfaces must be dry, sound and free of all bond inhibiting substances. Prepare surfaces in accordance with industry standards and manufacturer's specific recommendations. Cleaned concrete surfaces should have a minimum strength of 250 psi in direct tension. Cleaned asphalt surfaces should have a minimum strength of 100 psi at 73 +/- 4 F in direct tension. Steel surfaces should be cleaned to "white metal" according to SSPC SP 5.

**Mixing:** Kemko 064 LV Utility Coat is a two-component system. The resin to hardener (Part A: Part B) mix ratio is 1:1, by volume. Premix the individual components before drawing from bulk packaging. Wear safety glasses and clean neoprene rubber gloves when handling the material. Transfer the appropriate quantities of Part A and Part B into a mixing container. Use quantities that can be applied before the potlife of the mixed material expires. Blend thoroughly using a Jiffy mixer blade attached to a low speed (350-750 rpm) electric or pneumatic drill. Proper mixing will take 2-3 minutes.

**Installing** as a Coating or Surfacing: Multiple coats (at least 2-3) are recommended to reduce the potential for holidays. Pour the mixed material onto the substrate and spread to the desired coverage rate with a V-notch trowel or squeegee. Allow the coating to become tacky to tack-free (3-6 hr @ 70 F) before applying the next coat. Avoid excessive cure times between coats. Aggregate, if used, must be broadcast onto the Kemko 064LV within 15 minutes of applying the coating. The recommended aggregate size is #6x12 or #8x16 mesh. Typical aggregate broadcast rates are 1.25-1.75 lb/sq ft.

**Yield as a Coating:** The following material estimates do not take into consideration material lost in mixing and application and excess material required for filling rough surfaces.

Coating Thickness, mil.	Coverage, square feet/gallon
15	107
20	80
25	64
30	53

**Clean-up:** All tools and equipment must be cleaned before the mixed material cures. Cleaning can be facilitated with a solvent such as acetone or heavy duty detergents. Cured material may be removed from equipment by soaking in an epoxy stripper.

## Typical Properties (1)

Property	Test Method	Value
Mix Ratio, A:B,     by vol by wt		1 : 1 100 : 79
Color:   Part A Part B Mixed	VISUAL	Gray or black Clear amber Gray or black
Weight per Gallon, lb:     Part A Part B Mixed	ASTM D 1475	9.8 7.8 8.8
Viscosity, cps ·     Part A Part B Mixed	ASTM D 2393	900 1400 1150
Gel Time, 200 g, minutes	ASTM D 2471	20
Thin film tack free time, hrs	ASTM D 1640	8
Tensile Strength, psi	ASTM D 638	1600
Elongation at Break, %	ASTM D 638	70
Taber Abraser, mg loss	ASTM D 4060	80 (2)

(1) Cure schedule, 7 days at 73 +/- 4 F and test temperature, 73 +/- 4 F.

(2) CS-17 wheels, 1000 g load, 1000 cycles.

aid instructions, READ CAREFULLY THE MATERIAL SAFETY DATA SHEETS AND CONTAINER WARNING LABELS. Part A: Liquid epoxy resin, HMIS Health Hazard Rating- 2 (Moderate Hazard). Warning! Causes eye and skin irritation. May cause allergic skin reaction, Harmful if swallowed. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling, Avoid prolonged or repeated contact with skin. Part B: Liquid epoxy hardener, HMIS Health Hazard Rating- 2 (Moderate Hazard). Contains alkaline amines. Warning! Causes severe eye and skin irritation, May cause allergic skin and respiratory reaction. Combustible, corrosive. Do not get in eyes or skin or on clothing. Avoid breathing vapor, Keep container closed. Use only with adequate ventilation. Wash thoroughly after handling. Keep away from heat and open flame.

**DISCLAIMER:** NO EXPRESS WARRANTY IS MADE WITH RESPECT TO THE RESULTS OF ANY USE OF THIS PRODUCT. NO IMPLIED WARRANTIES, INCLUDING AND NOT LIMITED TO AN IMPLIED WARRANTY OF MERCHANTABILITY OR AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE ARE MADE WITH RESPECT TO THIS PRODUCT. NO LIABILITIES FOR PERSONAL INJURY, LOSS OR DAMAGE RESULTING FROM THE USE OF THIS PRODUCT IS ASSUMED.